

schedule 20 for Plain-End Pipe
(Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
200	8	219.1	8.625	6.35	0.250	33.32	22.38		20
250	10	273.0	10.750	6.35	0.250	41.76	28.06		20
300	12	323.8	12.750	6.35	0.250	49.71	33.41		20
350	14	355.6	14.000	7.92	0.312	67.91	45.65		20
400	16	406.4	16.000	7.92	0.312	77.83	52.32		20
450	18	457	18.000	7.92	0.312	87.71	58.9g		20
500	20	508	20.000	9.53	0.375	117.15	78.67	STD	20
550	22	559	22.000	9.53	0.375	129.14	86.69	STD	20
600	24	610	24.000	9.53	0.375	141.12	94.71	STD	20
650	26	660	26.000	12.7	0.500	202.74	136.30	XS	20
700	28	711	28.000	12.7	0.500	218.71	146.99	XS	20
750	30	762	30.000	12.7	0.500	234.68	157.68	XS	20
800	32	813	32.000	12.7	0.500	250.65	168.37	XS	20
850	34	864	34.000	12.7	0.500	266.63	179.06	XS	20
900	36	914	36.000	12.7	0.500	282.29	189.75	XS	20